

Aluminium and Aluminium alloys according to UNE EN 485:2009

DESIGNATION	TEMPER	MINIMUM YIELD STRESS (Re)	TENSILE STRENGTH (Rm)	MINIMUM ELONGATION (%)	Designations according to other standards
AW 5083	H0/H111/H22/H32	125	275-350	15	AlMg 4,5Mn, D54S, GM 41
AW 5754-TREAD PLATE	H111 /H114	80	190-260	12	AlMg 4,5Mn, D54S, GM 41
AW 1050A	H0/H111	75	05-145	5	Al-99,5, L-3051, 17010
AW 6082	T6	255	300	9	AlSiMgMn, L-3453, 3571, F177
AW 5754	H0/H111/H22/H32	80	190-240	18	AlMg3, 57S, AG3, GA6533